

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C07F 19/00, C23C 16/00	A1	(11) International Publication Number: WO 98/46617 (43) International Publication Date: 22 October 1998 (22.10.98)
(21) International Application Number: PCT/US98/07829 (22) International Filing Date: 17 April 1998 (17.04.98) (30) Priority Data: 60/043,279 17 April 1997 (17.04.97) US (71) Applicant: THE PRESIDENT AND FELLOWS OF HARVARD COLLEGE [US/US]; 12 Oxford Street, Cambridge, MA 02138-5701 (US). (72) Inventor: GORDON, Roy, G.; 22 Highland Street, Cambridge, MA 02138 (US). (74) Agent: SCOZZAFAVA, Mary, Rose; Choate, Hall & Stewart, Exchange Place, 53 State Street, Boston, MA 02109 (US).		(81) Designated States: CA, JP, KR, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: LIQUID PRECURSOR FOR FORMATION OF METAL OXIDES (57) Abstract A liquid precursor is provided for the formation of metal oxide films comprising a mixture of two or more types of beta-diketonate ligands bound to one or more metals. For example, a liquid mixture was formed of the mixed aluminum beta-diketonates derived from two or more of the ligands 2,6-dimethyl-3,5-heptanedione; 2,7-dimethyl-3,5-heptanedione; 2,6-dimethyl-3,5-octanedione; 2,2,6-trimethyl-3,5-heptanedione; 2,8-dimethyl-4,6-nonanedione; 2,7-dimethyl-4,6-nonanedione; 2,2,7-trimethyl-3,5-octanedione; and 2,2,6-trimethyl-3,5-octanedione. Films of metal oxides are deposited from vaporized precursor mixtures of metal beta-diketonates and, optionally, oxygen or other sources of oxygen. This process may be used to deposit high-purity, transparent metal oxide films on a substrate. The liquid mixtures may also be used for spray coating, spin coating and sol-gel deposition of materials.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

LIQUID PRECURSOR FOR FORMATION OF METAL OXIDES

This invention was made with the support of the United States government under National Science Foundation Grant No. NSF CHE-95-10245. The United States may have certain rights in the invention.

Background of the Invention

1. Field of the Invention

This invention relates to novel volatile liquid reagents which can replace less satisfactory solid sources in film deposition processes such as chemical vapor deposition (CVD), spray coating, spin coating or sol-gel deposition. These liquid reagents can be used for deposition of metals or metal-containing materials, such as metal oxides.

2. Description of the Related Art

Chemical vapor deposition (CVD) is a widely-used process for forming solid materials, such as coatings or powders, from reactants in the vapor phase.

Comprehensive reviews of CVD processes have been given recently in "CVD of Nonmetals," W. S. Rees, Jr., Editor, VCH Publishers, Weinheim, Germany, 1996; "CVD of Compound Semiconductors," A. C. Jones and P. O'Brien, VCH, 1996; and "The Chemistry of Metal CVD," T. Kotas and M. Hampden-Smith, Editors, VCH, 1994.

In CVD processes, a reactant vapor may be created by heating a liquid to a sufficiently high temperature and bubbling a flow of a carrier gas through the liquid, to transport the vapor into the CVD chamber. In a low-pressure CVD system, the

carrier gas may be omitted, and the vapor may flow directly from the bubbler into the low-pressure CVD chamber.

In order for a CVD process to function successfully, it is necessary to create a vapor containing controlled amounts of suitably reactive chemicals. Solids can be used as sources of vapor in CVD processes. However, when solids are used in a bubbler, the rate of vapor production by sublimation of a solid is not easily reproducible, because the amount of vapor produced often depends on the particle size and shape, which change as the sublimation process continues. Thus the vapor concentration can change in an uncontrolled way, thereby changing the growth rate and/or the composition of materials made by the CVD process. Also, different batches of solid may have different sizes and shapes of particles, so that the results of a CVD process may change when a new batch of solid precursor is placed in the system. These difficulties are particularly evident in the currently-used CVD precursors for barium, strontium and calcium, which are reviewed by W. A. Wojtczak, P. F. Fleig and M. J. Hampden-Smith, in *Advances in Organometallic Chemistry*, vol. 40, pp. 215-340 (1996).

Another problem with solids is that their rate of sublimation can be altered by small amounts of contamination on their surfaces. In contrast, liquid surfaces tend to be refreshed by motion of the liquid, so that they tend to evaporate at a reproducible rate even in the presence of small amounts of contaminants.

Some solid materials show different vapor pressures, depending on the history of how the particular sample was prepared. For example, aluminum isopropoxide has been used to deposit aluminum oxide films, for example by J. A. Aboaf in the *Journal of the Electrochemical Society*, vol. 114, pp. 948-952 (1967). Solid aluminum

isopropoxide exists in a number of isomeric forms, ranging from dimers to trimers to tetramers to polymers of various lengths. The rates of interconversion between isomeric forms are slow, often taking days. The vapor pressures of these isomers vary widely. Thus it is very difficult to regulate or predict the vapor pressure of any particular sample of aluminum isopropoxide, and the deposition rate of aluminum oxide from this solid source is not reproducible. In comparison, liquids usually exist in only one reproducible form at any given temperature and pressure.

Another difficulty with solids is that rates of sublimation are often low, so that sufficiently high vapor concentrations cannot be produced. For example, aluminum 2-ethylhexanoate has been proposed as a source for CVD of aluminum oxide, by T. Maruyama and T. Nakai in *Applied Physics Letters*, vol. 58, pp. 2079-2080 (1991). This solid source material has a very low vapor pressure, which limits the deposition rate to very low values. In comparison, liquids often have higher vapor pressures than solids.

Another practical difficulty with solids is that transferring them between containers is less convenient than pumping liquids.

Thermal decomposition of solids is another problem that often affects the reproducibility of solid vapor sources. For example, the solid beta-diketonates of barium and strontium gradually decompose at their vaporization temperatures, so that the amount of vapor generated decreases with time. Thermal decomposition is also a potential problem for liquid sources, but its effect may be minimized for liquids by rapid or "flash" vaporization. This can be accomplished by pumping the liquid at a steady, controlled rate into a hot region in which the liquid vaporizes quickly. In such a "direct liquid injection" (DLI) system, each part of the liquid is heated for only a

short time, and its vapor can be formed without significant decomposition even from thermally sensitive liquids. Another advantage of a DLI system is that multicomponent mixtures can be vaporized in a fixed and reproducible ratio, even if the components differ in volatility. Because of these advantages, DLI systems are becoming more widely used in CVD processes.

Solid sources can be used in DLI vapor sources if a suitable liquid solvent can be found to dissolve the solid. However, solvents can introduce other difficulties, such as increased flammability, toxicity or corrosiveness, and an increased volume of gaseous byproducts must be removed from the exhaust gases to avoid pollution.

These difficulties with a solvent can be minimized if the solid is highly soluble in the solvent, so that only a small amount of solvent is needed to form the liquid solution.

Because of all these difficulties, solid sources of vapor are seldom used in commercial CVD processes. Either liquids, or solids that are highly soluble in a liquid solvent, are more convenient, and more commonly used in the practice of CVD.

Creating this vapor from a liquid source would be much more reproducible and convenient than creating it from a solid source; however, there are few practical compounds which may be used for this purpose.

Beta-diketonates are one class of solid compounds that can be formed from almost every metal. Beta-diketonates are known for zinc, cadmium, mercury, aluminum, gallium, indium, thallium, tin, lead, antimony, bismuth, lithium, sodium, potassium, rubidium, cesium, beryllium, magnesium, calcium, strontium, barium, scandium, yttrium, lanthanum, titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum, tungsten, manganese, technetium, rhenium, iron, ruthenium, osmium, cobalt, rhodium, iridium, nickel, palladium, platinum, copper,

silver, cerium, the other rare earth metals and the actinide metals. A thorough review of beta-diketonate compounds was written by A. R. Siedle, in "Comprehensive Coordination Chemistry" (Pergamon Press, Oxford, 1987, vol. 2 chapter 15.4).

Almost all of the known beta-diketonate compounds are solids at room temperature,

5 and thus are not very convenient for use as vapor sources for CVD processes.

The vapor pressures of some of the solid beta-diketonates are low, even at temperatures high enough to cause their thermal decomposition. This problem is acute for the beta-diketonates of alkaline earth metals. Their vapor pressures may be increased by vaporizing them in the presence of amines (R. G. Gordon et al., U.S. Patent 5,139,999, 1992), ethers (Miller et al., U.S. Patent 4,501,602, 1985; Timmer et al., U.S. Patent 5,248,787, 1993; Kirlin et al., U.S. Patent 5,280,012, 1994) or thioethers (Kirlin et al., U.S. Patent 5,225,561, 1993). However, even when bound to these Lewis bases, the beta-diketonates disclosed in these references are still solids at room temperature.

15

Summary of the Invention

A principal object of the present invention to provide chemical precursors that are liquids at room temperature, or that are solids highly soluble in solvents, for the deposition of metal-containing materials.

An additional object of the present invention is to provide chemical precursors
20 that are easily vaporized without decomposition, and that do not leave a nonvolatile residue for the deposition of metal-containing materials.

A related object of the present invention is the deposition of metal-containing materials from chemical precursors that are liquids at room temperature, or that are solids highly soluble in solvents.

Another related object is to deposit materials containing several metals by a chemical vapor deposition process in which all the reactants may be mixed homogeneously before delivery to the heated surface of the substrate.

5 An additional object of the present invention is the deposition of metal-containing materials from chemical precursors that are easily vaporized without decomposition, and that do not leave a nonvolatile residue.

Another object of the present invention is to provide a process for making metal oxides having high purity.

10 Another object of the present invention is the deposition of metal oxide films from chemical precursors that are not pyrophoric.

A further object of the present invention is to deposit metal oxides from a robust chemical vapor deposition process which is not easily disrupted by leaks of air into the deposition region.

15 Another object of the invention is to provide a chemical vapor deposition process for metal oxides from reactants that are stable and relatively nonhazardous.

Another object of the invention is to provide a chemical vapor or solution deposition process for complex metal oxides in which the precursor metal-containing compounds are stable and homogeneous.

20 A further object of the invention is to provide liquid mixtures or solutions suitable for spray coating, spin coating or sol-gel deposition.

One particular object of the present invention is to provide a process for depositing aluminum oxide having high purity, high electrical resistivity and high transparency to light.

Another particular object of the present invention is to provide a process for depositing zirconium oxide having high purity, high electrical resistivity and high transparency to light.

5 A further particular object of the present invention is to provide a process for depositing zinc oxide having high purity, high electrical conductivity and high transparency to light.

Another particular object of the present invention is to provide a process for depositing barium ferrites having useful magnetic properties.

10 Another particular object of the present invention is to provide a process for depositing barium titanate having good ferroelectric properties.

Another particular object of the present invention is to provide a process for depositing strontium bismuth tantalate films having good ferroelectric properties.

15 Another particular object of the present invention is to provide a process for depositing barium-strontium titanate coatings having a high dielectric constant and a high electrical resistance.

Another particular object of the present invention is to provide a process for depositing a mixture of the oxides of iron, cobalt and chromium having low transparency to light.

20 Other objects of the invention will be obvious to those skilled in the art on reading the instant invention.

The above objects have been substantially achieved by use of a composition comprising a metal beta-diketonate having two or more types of beta-diketonate ligands bound to the metal. In preferred embodiments, the composition may be a mixture of metal beta-diketonate compounds in which at least one compound is a

metal beta-diketonate having two or more types of beta-diketonate ligands bound to the metal. The mixture may further comprise metal beta-diketonate compounds having the same beta-diketonate ligand bound to the metal. The metal beta-diketonate mixture may further contain two or more metal-types.

5 In a preferred embodiment, the beta-diketonate has the formula,
 $R^1C(=O)CHR^3C(=O)R^2$, where R^1 and R^2 may be an alkyl group, a fluoroalkyl group or an alkyl group containing oxygen- or nitrogen-containing species (for example, an amino, alcohol or alkoxyl species). R^3 may be an alkyl group, a fluoroalkyl group or an alkyl group containing oxygen- or nitrogen-containing species or H. In preferred
10 embodiments, the alkyl group contains less than ten carbons and preferably less than seven carbons. One preferred composition of the metal diketonates includes two or more ligands derived from 2,6-dimethyl-3,5-heptanedione; 2,7-dimethyl-3,5-heptanedione; 2,6-dimethyl-3,5-octanedione; 2,2,6-trimethyl-3,5-heptanedione; 2,8-dimethyl-4,6-nonanedione; 2,7-dimethyl-4,6-nonanedione; 2,2,7-trimethyl-3,5-
15 octanedione, and 2,2,6-trimethyl-3,5-octanedione.

 In preferred embodiments, the mixture of metal beta-diketonates is a liquid. It is believed that the use of a mixture in which a portion of the metal beta-diketonate compounds contain two or more different types of beta-diketonate ligands promotes the formation of the liquid phase.

20 In another embodiment of the invention, the mixture of metal beta-diketonates is a solid which is highly soluble in organic solvents. The metal beta-diketonate mixture may preferably be prepared in concentrations of greater than 0.1 M, more preferably greater than 0.5 M and most preferably greater than 1.0 M.

In some cases, only two different beta-diketonate ligands may be sufficient to achieve the properties cited above. In other cases, three or four or even more different ligands may be desired. Some embodiments may include six or more beta-diketonate ligands.

5 In another aspect of the invention, a process for the chemical vapor deposition of metal oxides from vapors of a mixture of metal beta-diketonates and, optionally, another oxygen-containing gas, is provided. The process may be used to form metal oxide films, including, but not limited to, aluminum oxide, zirconium oxide and zinc oxide. A preferred embodiment uses a homogeneous vapor mixture comprising these
10 ligands chelated to one or more metals, oxygen and, optionally, an inert carrier gas such as nitrogen. This vapor mixture is brought into contact with a substrate heated to a temperature sufficient to deposit a metal oxide. Typical deposition temperatures lie in the range of about 200 to 800 °C. Typical deposition pressures range from normal atmospheric pressure down to a few milli-Torr.

15 Another preferred embodiment uses a homogeneous liquid mixture of metal compounds having the metals bound to two or more beta-diketonates, and optionally, a solvent. This liquid mixture is vaporized to form a vapor mixture and, optionally mixed with an oxygen-containing gas, such as air, and an inert carrier gas such as nitrogen. This vapor mixture is heated to a temperature in sufficient to cause reaction
20 and the formation of a material comprising one or more metal oxides. Alternatively, reaction may be caused by light, or by the electrical energy of a plasma discharge.

In another embodiment of the invention, multimetal oxides are formed from mixtures of metal beta-diketones, in which the metal beta-diketonate mixture contains two or more metals, in deposition processes as described herein. The

process may be used to form multimetal oxide films, including, but not limited to, barium ferrites, barium titanate, strontium bismuth tantalate and barium strontium titanate.

Detailed Description of the Invention

5 The required beta-diketone ligands may be prepared by known methods, such as the Claisen condensation of a methyl ketone and an ethyl ester, in the presence of a strong base, such as sodium hydride. Detailed description of this procedure is given in *Inorganic Syntheses*, Vol. 23, pp. 144-145 (1985). The individual beta-diketones may be prepared separately and then mixed before combining them with the metal. A
10 quicker procedure is to condense simultaneously a mixture of methyl ketones, such as *tert*-butyl methyl ketone, *sec*-butyl methyl ketone, isobutyl methyl ketone and methyl isopropyl ketone, along with a mixture of ethyl esters, such as ethyl isobutyrate, ethyl isovalerate, ethyl 2-methylbutyrate and ethyl trimethylacetate. By proton-decoupled carbon-13 NMR analysis in deuteriochloroform, the resulting reaction product was
15 found to be a mixture containing ten of the preferred beta-diketone ligands. Table 1 gives the chemical shifts of the central carbon between the ketone groups, in the major (enol) forms of these ten compounds (the first 10 of Table 1) and some similar compounds. This single resonance line is easily resolved for each compound in this mixture, making it useful for analysis, whereas other lines in the proton and C-13
20 NMR spectra are badly overlapped. Table 1 also gives the numbers assigned by Chemical Abstracts to the previously reported compounds. The general formula is written $R^1C(=O)CHR^3C(=O)R^2$, where $R^3 = H$ in all these examples, where R^1 and R^2 may be an alkyl group, a fluoroalkyl group or an alkyl group containing oxygen- or nitrogen-containing species (for example, an amino, alcohol or alkoxyl species). R^3

may be an alkyl group, a fluoroalkyl group or an alkyl group containing oxygen- or nitrogen-containing species or H. In preferred embodiments, the alkyl group contains less than ten carbons and preferably less than seven carbons.

Table 1. Some beta-diketones

	Name	R ¹	R ²	Chemical Shift C-13 NMR, ppm	Chemical Abstracts No.
5	2,6-dimethyl-3,5-heptanedione	iso-Pr	iso-Pr	94.9	57733-60-5
	2,7-dimethyl-3,5-octanedione	iso-Pr	iso-Bu	97.8	7307-07-5
10	2,6-dimethyl-3,5-octanedione	iso-Pr	sec-Bu	96.0	not reported
	2,2,6-trimethyl-3,5-heptanedione	iso-Pr	tert-Bu	92.9	7333-23-5
15	2,8-dimethyl-4,6-nonanedione	iso-Bu	iso-Bu	100.6	7307-08-6
	2,7-dimethyl-4,6-nonanedione	iso-Bu	sec-Bu	98.8	not reported
	2,2,7-trimethyl-3,5-octanedione	iso-Bu	tert-Bu	95.7	69725-37-7
20	3,7-dimethyl-4,6-nonanedione	sec-Bu	sec-Bu	97.0	43865-74-2
	2,2,6-trimethyl-3,5-octanedione	sec-Bu	tert-Bu	94.0	34865-71-9
25	2,2,6,6-tetramethyl-3,5-heptanedione	tert-Bu	tert-Bu	90.6	1118-71-4
	2,2,6,6-tetramethyl-3,5-octanedione	tert-Bu	¹ pentyl	91.7	78579-61-0
30	6-ethyl-2,2-dimethyl-3,5-octanedione	tert-Bu	3-pentyl	95.4	188530-39-4
	2,2,6-trimethyl-3,5-nonanedione	tert-Bu	2-pentyl	93.9	not reported
35	6-ethyl-2,2-dimethyl-3,5-decanedione	tert-Bu	3-heptyl	95.3	not reported
40	3,3,7,7-tetramethyl-4,6-nonanedione	¹ pentyl	¹ pentyl		138024-17-6

Compounds can be formed between these ligands and most metals. One ligand can be bound to metal ions in oxidation state +1, such as copper, silver, thallium, lithium and sodium. Two ligands can be bound to metal ions in oxidation state +2, including copper, zinc, cadmium, mercury, tin, lead, beryllium, magnesium, calcium, strontium, barium, manganese, iron, cobalt, nickel, palladium and platinum. Three ligands can be bound to metals in oxidation state +3, including aluminum, gallium, indium, thallium, bismuth, titanium, vanadium, chromium, molybdenum, manganese, iron, ruthenium, cobalt, rhodium, iridium, scandium, yttrium, lanthanum, cerium, and the other rare earth metals. Four ligands can be bound to large metals in oxidation state +4, including titanium, zirconium, hafnium, niobium, cerium, thorium and uranium. Many different reactions can be used to bind beta-diketonate ligands to metals. Specific examples of preparative procedures are given in Inorganic Syntheses, for chromium(III) in Vol. 5, pp. 130-131 (1957) and Vol. 24, pp. 183-184 (1986); for cobalt(III) in Vol. 5, pp. 188-189 (1957); for rare earth metals in Vol. 11, pp. 94-98 (1968); for cerium(IV) in Vol. 12, pp. 77-78 (1970) and Vol. 23, pp. 147-8 (1985); for manganese(III) in Vol. 23, pp. 148-149 (1985); for iron(II) in Vol. 31, pp. 267-269 (1997); for copper(II) in Vol. 23, pp. 146-147 (1985); for beryllium in Vol. 2, pp. 17-20 (1946); and for calcium, strontium and barium in Vol. 31, pp. 1-7 (1997). The distribution of metal beta-diketonates will depend on the number and relative amounts of beta-diketonate types used in the preparation of the metal compounds.

Additional ligands, besides the beta-diketonate mixtures, may be advantageously bound to the metal. For example, the barium, strontium or calcium mixed beta-diketonates may be complexed with donor solvents, such as ethers or amines. Metals in higher oxidation states, such as titanium(IV) or tantalum(V), may

contain monodentate ligands, such as alkoxides or halides, in addition to the mixed beta-diketonate ligands.

Some or all of the oxygens in the beta-diketonate ligands may be replaced by isoelectronic species, such as sulfur or NH or NR, where R is a hydrocarbon radical.

- 5 Ligands with these sulfur or nitrogen replacements are particularly useful in binding heavy metals, such as platinum or mercury. For the purposes of this specification and claims, these isoelectronically substituted beta-diketonate ligands shall be considered as beta-diketonates.

- Some or all of the hydrogens in the beta-diketonate ligands may be replaced
10 by fluorine. Fluorine substitution may be used to deposit fluorides instead of oxides. Fluorine substitution may also provide higher vapor pressures of the precursor compounds.

- The novel metal beta-diketonate mixtures of this invention are generally liquids or highly soluble glasses at room temperature. The vapor of these liquid
15 mixtures may be formed in a thin-film evaporator, or by nebulization into a carrier gas preheated to about 150 to 250 °C. The nebulization may be carried out pneumatically or ultrasonically. Alternatively, the mixture may be dissolved in a solvent and the liquid solution vaporized using a thin film evaporator or nebulization. The liquid metal beta-diketonate mixtures are generally completely miscible with organic
20 solvents, including hydrocarbons, such as dodecane, tetradecane, and xylene, and with alcohols, ethers, esters, ketones and chlorinated hydrocarbons. The solid glassy metal beta-diketonate mixtures are generally highly soluble in organic solvents.

The process of the invention can be carried out in standard equipment well known in the art of chemical vapor deposition. The apparatus brings the vapors of the

reactants into contact with a heated substrate on which the metal oxide deposits. The process can operate at a variety of pressures, including in particular normal atmospheric pressure, and also lower pressures. Commercial atmospheric pressure CVD furnaces are made in the USA by the Watkins-Johnson Company (Scotts Valley, California), BTU International (North Billerica, Massachusetts) and SierraTherm (Watsonville, California). Commercial atmospheric pressure CVD equipment for coating glass on the float production line is made in the USA by the Libbey-Owens-Ford Company (Toledo, Ohio), PPG Industries (Pittsburgh, Pennsylvania) and AFG Industries (Kingsport, Tennessee). Low-pressure CVD equipment is made by Applied Materials (Santa Clara, California), Spire Corporation (Bedford, Massachusetts), Materials Research Corporation (Gilbert, Arizona), Novellus (San Jose, California) and Emcore Corporation (Somerset, NJ).

The liquid or solid reactants may be vaporized by well-known methods, including passing a carrier gas through a heated liquid or powdered solid in a bubbler, or injecting or spraying a liquid or a solution into a flow of heated carrier gas. Commercial equipment for direct vaporization of liquids (DLI) is made by MKS Instruments (Andover, Massachusetts), ATMI (Danbury, Connecticut), Novellus (San Jose, California) and COVA Technologies (Tiburon, California). Thin-film evaporators are made by Artisan Industries (Waltham, Massachusetts).

The liquids and solutions described herein may also be used as metal-containing precursors for other types of deposition processes, such as spray coating, spin coating or sol-gel formation of mixed metal oxides. The high solubility and miscibility of these precursors is an advantage in forming the required solutions. The fact that a common set of ligands may be used with a wide variety of metals, means

that solutions of different metal precursors may be mixed with little chance for undesired precipitation of insoluble byproducts.

All experimental manipulations were carried out using standard Schlenk techniques under dry nitrogen either in a glovebox or on a Schlenk line unless
5 otherwise stated.

EXAMPLE 1

A mixture of beta-diketones was first prepared by condensing a mixture of ethyl esters and methyl ketones with sodium hydride as a strong base. 350 ml of toluene was dried by distillation from sodium, and placed in a 1-liter flask with three
10 necks. 1.4 moles of NaH (59 g of 60 weight % dispersion in mineral oil) was added to the toluene. To this mixture was added 20.33 g (0.175 mol) of ethyl isobutyrate, 22.78 g (0.175 mol) of ethyl isovalerate, and 45.57 g (0.35 mol) of ethyl 2-methyl butyrate. This mixture was stirred rapidly and heated in a water bath to nearly 100 °C. Dry nitrogen was passed slowly into the flask from one of the three necks. A water-
15 cooled reflux condenser was placed in a second of the three necks. A pressure-equalized dropping funnel was placed in the third neck. In the dropping funnel was placed 23.37 g (0.23 mol) of methyl tert-butyl ketone, 20.10 g (0.23 mol) of methyl iso-propyl ketone and 23.37 g (0.23 mol) of methyl iso-butyl ketone. The ketone mixture was added slowly (dropwise) with vigorous stirring, over a period of three
20 hours. Heating was continued for 30 minutes, and then the mixture was allowed to cool to room temperature, and the stirring was continued overnight. Then the mixture was then cooled in an ice-bath and neutralized by slow addition of 6M hydrochloric acid (about 300 ml). (Caution, flammable hydrogen gas is evolved.) The mixture was filtered to remove suspended solids, which were discarded. The mixture was put in a

separatory funnel, and the organic layer isolated. The toluene was removed in a rotary evaporator. The crude beta-diketonates were then dried with magnesium sulfate and distilled under reduced pressure, to separate them from the mineral oil and other high-boiling impurities. 93.16 g (60 % yield) of a light yellow liquid was
5 obtained.

This beta-diketonate mixture was analyzed by carbon-13 NMR. It contained the expected eight compounds, 2,6-dimethyl-3,5-heptanedione; 2,7-dimethyl-3,5-heptanedione; 2,6-dimethyl-3,5-octanedione; 2,2,6-trimethyl-3,5-heptanedione; 2,8-dimethyl-4,6-nonanedione; 2,7-dimethyl-4,6-nonanedione; 2,2,7-trimethyl-3,5-octanedione, and 2,2,6-trimethyl-3,5-octanedione. The carbon-13 resonances were
10 identified by separate syntheses of each of the pure components by analogous methods. The best-isolated resonance peaks were from the carbon between the ketone groups, in the enol form, which is the major isomer of these compounds.

The beta-diketones in this mixture were attached to aluminum by reaction with triethylaluminum. 5.25 g (0.03 mol) of the beta-diketone mixture was dissolved in 15
15 ml of dry benzene, in a magnetically-stirred Schlenk flask that was cooled in an ice-bath. 1.14 g (0.01 mol) of triethylaluminum was dissolved in 25 ml of dry benzene, and added dropwise over 1 hour to the cooled solution of beta-diketonates. Ethane gas was evolved during the addition, and passed out of a protective oil bubbler
20 attached to the Schlenk flask. The reaction mixture remained clear until about 85 % of the triethylaluminum had been added, after which some white solid precipitate gradually formed. The solution was filtered to remove the undesired solid precipitate. The liquid solution was placed under vacuum and heated to remove the benzene

solvent and excess beta-diketone. The product was 4.4 g (80% yield) of a pale yellow liquid aluminum beta-diketonate mixture.

This aluminum beta-diketonate mixture was vaporized by pumping the liquid at a rate of 0.05 milliliters per minute into a pneumatic nebulizer together with a flow of 8 liters per minute of dry nitrogen gas preheated to a temperature of 180 °C. A separate gas mixture was formed by the flow of 1 liter per minute of dry oxygen and 2 liters per minute of dry nitrogen. These two vapor mixtures were combined at a tee joint, from which they flowed through a line heated to 180 °C into the entrance to an atmospheric pressure CVD chamber measuring 10 cm wide by 0.6 cm high by 10 cm long (in the direction of the gas flow). A glass substrate rested on the bottom of the CVD chamber, which is heated from below, so that the glass plate was held at a temperature of about 450 °C, while the top plate of the CVD chamber was at about 250 °C. Prior to the deposition and while the glass plate was heating up, dry nitrogen passed through the chamber. Valves then switched on the flows of aluminum diketonate mixture and oxygen through the chamber for one minute, during which a layer of aluminum oxide was deposited.

On the surface of the glass plate there was a transparent film. The film was determined to be aluminum oxide, Al_2O_3 , by Rutherford Backscattering Analysis (RBS) and X-ray Photoelectron Spectroscopy (XPS). Its structure is amorphous by X-ray diffraction. The film has a refractive index of about 1.6, a dielectric constant of about 6 to 8, and a very high electrical resistance. The absorption of visible light by the film is less than 0.1 per cent. It is a good barrier to the diffusion of most materials, including sodium ions and water.

EXAMPLE 2

A zinc beta-diketonate mixture was formed by reaction of the beta-diketone mixture made in Example 1 with zinc acetate. 10.5 g (0.057 mol) of anhydrous zinc acetate and 25 ml of anhydrous ethanol were placed in a 100 ml glass flask fitted with a reflux condenser, heated to reflux, and magnetically stirred. 25 g (0.144 mol) of the beta-diketone mixture was added to the solution, and refluxing was continued for 2 hours. The pressure was reduced in order to distill out the ethanol, acetic acid byproduct and excess beta-diketone mixture. 18.7 g (80 % yield, based on the zinc acetate) of a very viscous yellow liquid zinc beta-diketonate mixture remained.

The zinc beta-diketonate mixture was dissolved in an equal weight of mesitylene, and this solution was pumped into a CVD reactor as described in Example 1. A transparent, electrically conductive coating of was formed. The film was determined to be zinc oxide, ZnO, by RBS and XPS. It is crystalline by X-ray diffraction. Its refractive index was measured to be about 1.9.

EXAMPLE 3

A barium beta-diketonate mixture was formed by reaction of barium hydride with the beta-diketone mixture made as in Example 1. 1.81 g (0.013 mol) of barium hydride was suspended in a solvent mixture containing 2.89 g (0.013 mol) of tetraglyme and 25 ml of hexane in a 100 ml glass flask, magnetically stirred and cooled in an ice bath. 4.55 g (0.026 mol) of the beta-diketone mixture was added dropwise to the suspension over a period of 1 hour. Hydrogen gas was evolved during the addition. The resulting slightly turbid mixture was filtered to remove the small amount of solid contaminant (probably traces of barium oxide or barium hydroxide impurity in the barium hydride). The pressure was reduced, and the hexane

distilled out. There remained 9 g of a yellow liquid containing a mixture of barium beta-diketonates.

This liquid barium beta-diketonate mixture was mixed with twice its weight of dry liquid dodecane. The purpose of the added dodecane solvent is to reduce the viscosity of the mixture, so that it can be vaporized more efficiently in an ultrasonic nebulizer. This dodecane solution was pumped at a 0.25 cc/min liquid flow rate into an ultrasonic nebulizer, through which nitrogen gas at 80 Torr pressure and 400 standard cc/min was passed. The resulting fog was mixed with a dry air flowing at 200 standard cc/min, and this combined mixture flowed at a pressure of 80 Torr into a tubular reactor (25 mm inside diameter) heated inside a tube furnace at 450 °C. A transparent coating was formed on glass and silicon substrates in the tube furnace, as well as on the inside wall of the tube. The film was determined to be barium carbonate, BaCO_3 , by RBS and XPS. Its refractive index was 1.6.

EXAMPLE 4

Example 3 was repeated with strontium hydride in place of the barium hydride. Similar results were obtained.

EXAMPLE 5

Example 3 was repeated with calcium hydride in place of the barium hydride. Similar results were obtained.

EXAMPLE 6

Titanium bis(isopropoxide) bis(mixed beta-diketonates) was formed by reaction of titanium isopropoxide with a mixture of beta-diketones. 14.2 g (0.05 mol) of titanium isopropoxide was placed in a 100 ml glass reaction flask, magnetically stirred and cooled in an ice-bath. 17.5 g (0.1 mol) of the beta-diketone mixture

prepared as in Example 1 was added slowly over a period of 1 hour. The reaction mixture turned dark yellow and then yellow-brown while remaining clear and non-turbid. The reaction mixture was allowed to warm to room temperature, the pressure was reduced, and byproduct isopropanol was distilled out of the mixture. 26 g of a
5 liquid titanium bis(isopropoxide) bis(mixed beta-diketonates) product was recovered.

The liquid titanium bis(isopropoxide) bis(mixed beta-diketonates) was pumped at a 0.10 cc/min liquid flow rate into an ultrasonic nebulizer, through which nitrogen gas at 80 Torr pressure and 400 standard cc/min was passed. The resulting fog was mixed with a dry air flowing at 200 standard cc/min, and this combined
10 mixture flowed at a pressure of 80 Torr into a tubular reactor (25 mm inside diameter) heated inside a tube furnace at 450 °C. A transparent coating was formed on glass and silicon substrates in the tube furnace, as well as on the inside wall of the tube. The film was determined to be titanium dioxide by RBS. The refractive index of the film was measured by ellipsometer to be 2.2.

15

EXAMPLE 7

Mixed beta-diketonates of titanium were formed by reaction of titanium isopropoxide with a mixture of beta-diketones. 14.2 g (0.05 mol) of titanium isopropoxide was placed in a 100 ml glass reaction flask, magnetically stirred and cooled in an ice-bath. 35 g (0.2 mol) of the beta-diketone mixture prepared as in
20 Example 1 was added slowly over a period of 1 hour. The reaction mixture turned dark yellow and then brown while remaining clear and non-turbid. The reaction mixture was allowed to warm to room temperature, the pressure was reduced, and byproduct isopropanol was distilled out of the mixture. 36 g of a titanium (mixed beta-diketonates) product was recovered. The exact stoichiometry of this product is

unknown, because some unreacted beta-diketones remained along with some bound isopropoxy groups.

The liquid titanium (mixed beta-diketonates) was used in a CVD experiment similar to that of Example 6, and similar results were obtained.

5

EXAMPLE 8

Zirconium tetra(mixed beta-diketonates) was formed by reaction of zirconium tetra(2,4-pentanedionate) with a mixture of beta-diketones. 8.22 g (0.0169 mol) of zirconium tetra(2,4-pentanedionate) was placed in a 100 ml glass reaction flask. 11.83 g (0.0676 mol) of the beta-diketone mixture prepared as in Example 1 was added, and the mixture was magnetically stirred and heated to 135 °C for 1 hour. During this time, the solid zirconium tetra(2,4-pentanedionate) dissolved to give a clear yellow solution. The pressure was reduced, and byproduct 2,4-pentanedione was distilled out of the mixture. 11 g (85 % yield) of the viscous liquid zirconium tetra(mixed beta-diketonates) product was recovered. The liquid is air-stable and miscible with organic solvents.

10

15

The liquid zirconium tetra(mixed beta-diketonates) was used as a precursor in a CVD experiment similar to that described in Example 1. The deposited film was determined to be zirconium dioxide, ZrO_2 , by RBS. The refractive index of the transparent film was measured by ellipsometer to be 2.0.

20

EXAMPLE 9

Tantalum (mixed beta-diketonate) tetra(ethoxide) was formed by reaction of tantalum ethoxide with a mixture of beta-diketones. 8.397 g (0.02067 mol) of tantalum(V) ethoxide was placed in a glass flask, magnetically stirred and cooled in an ice-bath. 3.61 g (0.0206 mol) of the beta-diketone mixture prepared as in Example

1 was added. The reaction mixture was stirred and heated to 65 °C for 2 hours. Then the pressure was reduced and byproduct isopropanol was distilled out of the mixture. 9.37 g (84 % yield) of clear, light yellow, low-viscosity liquid tantalum (mixed beta-diketonates) tetra(ethoxide) product was recovered.

5 The liquid tantalum (mixed beta-diketonates) tetra(ethoxide) was pumped at a
0.10 cc/min liquid flow rate into an ultrasonic nebulizer, through which nitrogen gas
at 80 Torr pressure and 400 standard cc/min was passed. The resulting fog was mixed
with a dry air flowing at 200 standard cc/min, and this combined mixture flowed at a
pressure of 80 Torr into a tubular reactor (25 mm inside diameter) heated inside a tube
10 furnace at 400 °C. A transparent, electrically insulating coating was formed on glass
and silicon substrates in the tube furnace, as well as on the inside walls of the tube.
The film was determined by RBS to be tantalum(V) oxide, Ta₂O₅, containing some
excess oxygen or hydroxide and no detectable carbon. The refractive index of the
film was measured by ellipsometer to be 2.2.

15 COMPARATIVE EXAMPLE 10

Example 9 was repeated with 2,4-pentanedione in place of the mixture of beta-diketonates. A solid material, tantalum (2,4-pentanedionate) tetra(ethoxide), was found instead of the liquid tantalum (mixed beta-diketonates) tetra(ethoxide).

EXAMPLE 11

20 Mixed beta-diketonates of magnesium were formed by reaction of magnesium ethoxide with a mixture of beta-diketones. 5.72 g (0.05 mol) of magnesium ethoxide was added to 25 ml of tetraglyme. 17.5 g (0.1 mol) of the beta-diketone mixture prepared in Example 1 was added, and the mixture was magnetically stirred and heated to 80°C for 1 hour. During this time, the solid magnesium ethoxide dissolved

to give a clear solution. The pressure was reduced, and byproduct ethanol was distilled out of the solution. The resulting solution was used in a CVD experiment similar to that of Example 3. A film of magnesium oxide, MgO, was obtained.

EXAMPLE 12

5 Equal molar quantities of the barium di(mixed beta-diketonates) from Example 3 and the titanium (mixed beta-diketonates) from Example 7 were dissolved in an equal weight of tetraglyme. This mixture was used in a CVD experiment similar to that of Example 3, to deposit a film of barium titanate, BaTiO₃.

COMPARATIVE EXAMPLE 13

10 Example 12 was repeated with titanium(IV) isopropoxide, a conventional source for CVD of titanium oxide, in place of the titanium (mixed beta-diketonates) from Example 7. A solid precipitate (probably a polymeric barium isopropoxide) formed immediately, and the mixture could not be used as a vapor source for CVD.

EXAMPLE 14

15 Synthesis of pentamethyldiethylenetriamine (pmdeta) adduct of mixed barium beta-diketonates, Ba(beta-diketonates)₂pmdeta. Ba (0.878 g, 6.39 mmol) and pmde-
ta (2.22 g, 12.8 mmol) were placed together in a flask and 7 mL of THF was added. Bubbles were evolved slowly upon addition of a beta-diketone mixture (2.26 g, 12.8 mmol) diluted with 7 mL of THF. The reaction, more intense after passing NH₃,
20 through the solution for 5 minutes, continued for 20 minutes until there was very little metal. The NH₃ flow was continued for another 5 minutes followed by 15 minutes of stirring until only flecks of metal remained. On addition of NH₃ to the solution the second time, a light green gel, perhaps Ba(beta-diketonate)₂(NH₃)_x, formed but slowly disappeared on stirring under flowing N₂. The solution was then filtered through

celite and the solvent was removed *in vacuo* to leave a light yellow liquid (4.16 g, 78%). This liquid was used in a CVD experiment similar to that of Example 3, to deposit a film of barium carbonate, BaCO_3 .

EXAMPLE 15

5 Example 14 was repeated with strontium in place of barium. Similar results were obtained.

EXAMPLE 16

Synthesis of mixed titanyl bis(beta-diketonates), $\text{TiO}(\text{beta-diketonates})_2$. A beta-diketone mixture (6.81 g, 38.6 mmol) diluted with 10 mL of THF was cannula-
10 transferred to $\text{Ti}(\text{O}^i\text{Pr})_4$ (5.48 g, 19.3 mmol) diluted with 20 mL of THF. The reaction produced heat and resulted in an amber-colored solution. After complete addition, H_2O (0.35 mL, 19.4 mmol) in 10 mL of THF was added dropwise. There was no noticeable color change. The solution was stirred 3 days, filtered and the solvent was removed in *vacuo* at 25 °C. After most of the solvent was removed, the product was
15 further evacuated at 80 °C for 20 minutes leaving a dark brown, viscous liquid (7.65 g, 96%). This liquid was used in a CVD experiment similar to that of Example 3, to deposit a transparent film of titanium dioxide, TiO_2 .

EXAMPLE 17

The precursors for barium, strontium and titanium made according to
20 Examples 14, 15 and 16 were mixed in the molar ratio 7:3:10 and used in a CVD experiment similar to Example 3, with a substrate temperature 500 °C. The resulting barium strontium titanate film contained significant carbon contamination, which was removed by annealing for 10 minutes at 600 °C in flowing oxygen gas.

EXAMPLE 18

Synthesis of mixed beta-diketonates of ruthenium(III), Ru(beta-diketonates)₃. RuCl₃·H₂O (1.81 g, 8.01 mmol) was suspended in 15 mL of EtOH and a beta-diketone mixture (4.23 g, 24.1 mmol) diluted with 7 mL of EtOH was added. Smoke was evolved upon dropwise addition of Et₃N (2.45 g, 24.2 mmol) diluted with 15 mL of EtOH. The solution was refluxed at 98 °C for 26 hours, the solvent was removed *in vacuo* and 30 mL of hexane was added. After filtration, the solvent was removed leaving a very dark red/brown, viscous liquid (4.07 g, 81.4%). This liquid was taken up in 3.20 g of mesitylene giving a 56% w/w solution. This solution did not show any appreciable change on exposure to air.

CVD was carried out with this solution as in Example 1. A film of metallic ruthenium(IV) dioxide, RuO₂, was produced with electrical resistivity about 1.4×10^{-4} ohm-cm. In the absence of oxygen, a similar deposition produced a film with composition RuO_{0.5}.

EXAMPLE 19

Synthesis of mixed yttrium tris(beta-diketonates), Y(beta-diketonates)₃. A beta-diketone mixture (16.85 g, 96.0 mmol) was diluted in 30 mL of EtOH and added to YCl₃ (5.01 g, 25.7 mmol) dissolved in 75 mL of EtOH. Some smoke was evolved upon dropwise addition of Et₃N (7.80 g, 77.1 mmol) diluted with 15 mL of EtOH and the solution eventually became yellow and cloudy. After stirring for hours, the EtOH was removed *in vacuo* at ambient temperature to leave white solid suspended in a yellow oil. To this was added 60 mL of hexane. After filtration, removal of the solvent *in vacuo* and further evacuation at 90 °C to remove excess beta-diketone, a viscous yellow liquid (11.19 g, 71%) remained. This liquid was used in a CVD

experiment similar to that of Example 1, to deposit a film of yttrium(III) oxide, Y_2O_3 , along with some excess oxygen or hydroxide and no detectable carbon.

EXAMPLE 20

Synthesis of mixed beta-diketonates of lanthanum, $La(\text{beta-diketonates})_3$. A
5 beta-diketone mixture (13.51 g, 77.0 mmol) was diluted in 30 mL of EtOH and added
to $LaCl_3$ (5.00 g, 20.4 mmol) dissolved in 100 mL of EtOH. Some smoke was
evolved upon dropwise addition of Et_3N (6.19 g, 61.2 mmol) diluted with 20 mL of
EtOH and the solution eventually became yellow. After stirring 12 hours, the EtOH
was removed *in vacuo* at ambient temperature to leave white solid suspended in a
10 yellow oil. To this was added 50 mL of hexane. After filtration, removal of the
solvent *in vacuo* and further evacuation at 90 °C to remove excess beta-diketone, a
very viscous yellow liquid (8.22 g, 61%) remained. This liquid was dissolved in
12.58 g of pmdeta to give a 40% w/w solution. This solution was used in a CVD
experiment similar to that of Example 1, to deposit a film of lanthanum oxide
15 containing some carbon impurity.

EXAMPLE 21

Synthesis of mixed beta-diketonates of manganese(III), $Mn(\text{beta-diketonates})_3$. Manganese tris(acetylacetonate), $Mn(\text{acac})_3$, (1.01 g, 2.87 mmol) and a
beta-diketone mixture (1.87 g, 10.7 mmol) were added together to a flask neat. The
20 flask was fitted with a reflux condenser and the very dark brown mixture was heated
to 130 °C when a colorless liquid (acacH) began to reflux. After heating for 1.5
hours, the acacH and excess beta-diketones were removed *in vacuo* at 130 °C leaving
a dark brown liquid which became a glassy solid (1.19 g, 72%) on cooling. The solid
was dissolved in 1.90 g of pmdeta to give a 39% w/w solution.

The resulting solution was used in a CVD experiment similar to that of Example 3. A film of manganese(III) oxide, Mn_2O_3 , was produced.

EXAMPLE 22

Synthesis of the tetramethylethylenediamine adduct of magnesium bis(beta-diketonate), $Mg(\text{beta-diketonate})_2 \cdot \text{tmeda}$. To magnesium ethoxide, $Mg(OEt)_2$, (5.00 g, 43.7 mmol) was added 125 mL dimethoxyethane (DME) and a beta-diketone mixture (16.86 g, 96.1 mmol). After refluxing 12 h at 90 °C, the volatile material and excess beta-diketones were removed *in vacuo* at 90 °C leaving a yellow glassy solid. This was dissolved in 20 g of tmeda, heated gently and then the volatiles were removed at ambient temperature giving a slightly-viscous yellow liquid (16.2 g, 75% yield).

The resulting solution was used in a CVD experiment similar to that of Example 3. A film of magnesium oxide, MgO , was produced.

EXAMPLE 23

Synthesis of mixed lead beta-diketonates, $Pb(\text{beta-diketonates})_2$. Lead(II) acetylacetonate, $Pb(\text{acac})_2$, (2.00 g, 4.94 mmol) and a beta-diketone mixture (1.74 g, 9.87 mmol) were added together to a flask neat to form a suspension of white solid in a yellow liquid. The suspension became a clear solution upon refluxing for 12 hours at 180 °C. After heating another 12 hours, the excess acacH was removed *in vacuo* at 90 °C leaving a dark brown glass. This product was dissolved in pmdeta. The resulting solution was used in a CVD experiment similar to that of Example 3. A film of lead oxide was produced.

EXAMPLE 24

Synthesis of mixed vanadyl bis(beta-diketonates), V(beta-diketonates)₂.

Vanadyl trichloride, VOCl₃, (0.92 g, 5.31 mmol) was cooled to 0 °C and 20 mL of EtOH was added dropwise giving an orange solution. Addition of a beta-diketone mixture (3.57 g, 20.3 mmol) diluted in 10 mL of EtOH gave a deep chocolate-brown solution. Addition of the first drops of Et₃N (1.77 g, 17.5 mmol) produced white smoke, and the solution began to turn red upon further addition. After complete addition and subsequent removal of the ice bath, the solution was deep red. The solution was stirred at ambient temperature for 12 hours and then the volatiles were removed *in vacuo*. Hexane (90 mL) was added, the solution was filtered and the volatiles were removed *in vacuo*. Further evacuation at 90 °C removed some excess beta-diketones and resulted in color change from deep red to black to blue to finally give an olive-colored glass (2.68 g, 133%). This solid was dissolved in 4.42 g of pmdeta giving a 38% w/w solution. The resulting solution was used in a CVD experiment similar to that of Example 3. A film of carbon-containing vanadium oxide was deposited.

EXAMPLE 25

Synthesis of nickel bis(beta-diketonate mixture), Ni(beta-diketonates)₂. A beta-diketone mixture (5.97 g, 34.0 mmol) was diluted in 10 mL of EtOH and added to NiCl₂ (2.00 g, 15.4 mmol) which was suspended in 30 mL of EtOH giving an orange solution with orange solid. Some smoke was evolved upon dropwise addition of Et₃N (3.14 g, 31.1 mmol) diluted with 10 mL of EtOH and the solution eventually became yellow-green. After stirring 12 hours, the solution had turned bright green. The EtOH was removed *in vacuo* at ambient temperature and 50 mL of hexane was

added. After filtration, removal of the solvent *in vacuo* and further evacuation at 90 °C to remove excess beta-diketones, a green glassy material (4.73 g, 75%) remained. This was dissolved in 6.9 g of pmdeta to give a 41% w/w solution. The resulting solution was used in a CVD experiment similar to that of Example 3. A film of nickel
5 oxide was produced.

EXAMPLE 26

Synthesis of the pentamethyldiethylenetriamine adduct of calcium bis(beta-diketonate mixture), $\text{Ca}(\text{beta-diketonates})_2\text{pmdeta}$. CaH_2 (2.01 g, 47.8 mmol) was suspended in pmdeta (17.30 g, 99.8 mmol) diluted with 10 mL of THF,
10 and a beta-diketone mixture (17.51 g, 99.8 mmol) diluted with 20 mL of THF was added. No bubbling occurred during addition, so the reaction was heated to reflux. Slow gas evolution was observable while heating, so the solution was refluxed 2 days until the solution no longer bubbled. The grey suspension was filtered and the solvent was removed *in vacuo* at 25 °C leaving a light yellow liquid (12.93g, 48%). The
15 resulting solution was used in a CVD experiment similar to that of Example 3. A film of calcium carbonate, CaCO_3 , was produced.

EXAMPLE 27

Synthesis of cerium tetrakis(beta-diketonate mixture), $\text{Ce}(\text{beta-diketonates})_4$. For the following reaction, all manipulations before solvent removal
20 were performed on a benchtop in air. $\text{Ce}(\text{NO}_3)_6\text{H}_2\text{O}$ (4.99 g, 16.1 mmol) was dissolved in 15 mL of MeOH and a beta-diketone mixture (8.08 g, 4.61 mmol) diluted with 25 mL of MeOH was added. 4 M NaOH was added slowly to the solution until the pH was 9, giving a dark red oil with no precipitate. The solution was extracted with 70 mL of hexane, and all of the colored material was taken up into the hexane

layer. The hexane layer was removed using a separatory funnel and the solvent was removed *in vacuo* leaving an oily, solid material (9.70 g, 63%). This was dissolved in mesitylene, and the resulting solution was used in a CVD experiment similar to that of Example 1. A film of cerium(IV) oxide, CeO_2 , was produced.

5

EXAMPLE 28

Synthesis of niobium(V) mixed beta-diketonates. Niobium(V) ethoxide, $\text{Nb}(\text{OEt})_5$ (3.99 g, 12.5 mmol), and a beta-diketone mixture (11.09 g, 63.2 mmol) were added together to a flask neat. This was warmed to 50 °C under a static partial vacuum until EtOH began to reflux and the solution color began to darken. When the color became a darker red, the volatiles were removed under dynamic vacuum until bubbling was no longer evident. This gave a deep-red liquid (12.26 g). Some ethoxide ligands remained, so the actual number of beta-diketone ligands is not known. The liquid was used in a CVD experiment similar to that of Example 3. A film of carbon-containing niobium oxide was deposited.

10

15

EXAMPLE 29

Synthesis of molybdenum mixed beta-diketonates, $\text{Mo}(\text{beta-diketonate})_5$. Dropwise addition of 20 mL of EtOH to MoCl_5 (1.50 g, 5.49 mmol) produced some smoke and heat. A beta-diketone mixture (4.83 g, 2.75 mmol) diluted in 20 mL of EtOH was added to this suspension. Addition of Et_3N (2.80 g, 2.77 mmol) produced much more smoke and a dark-brown solution. After stirring 5 hours, the volatiles were removed *in vacuo* and 60 mL of hexane was added. The solution was filtered and the volatiles were removed *in vacuo* leaving a very viscous, dark-brown liquid (2.96 g, 55%). This product was diluted with mesitylene, and the resulting solution

20

was used in a CVD experiment similar to that of Example 3. A film of molybdenum oxide was formed.

EXAMPLE 30

Synthesis of mixed copper(II) beta-diketonates, $\text{Cu}(\text{beta-diketonates})_2$.

- 5 For the following reaction, all manipulations before solvent removal were performed on a benchtop in air. Copper(II) acetate, $\text{Cu}(\text{OAc})_2 \cdot \text{H}_2\text{O}$, was dissolved in 75 mL of boiling water and passed through a filter into a stirring solution of 20 mL of a beta-diketone mixture in 20 mL of MeOH. After stirring 5 minutes, a dark-blue hydrophobic mass had formed. This was extracted with 40 mL of hexane and
- 10 separated from the colorless aqueous layer with a separatory funnel. Removal of the solvent *in vacuo* left a dark-blue solid with light-blue solid present. The solid was dissolved in 20 mL of hexane and filtered to remove some of the $\text{Cu}(\text{OAc})_2 \cdot \text{H}_2\text{O}$ impurity present. Removal of the solvent left a dark-blue solid (15.06 g) still showing evidence of $\text{Cu}(\text{OAc})_2 \cdot \text{H}_2\text{O}$ impurity. The solid was dissolved in a minimal amount of
- 15 decane and filtered again leaving behind a fairly large amount of light blue solid ($\text{Cu}(\text{OAc})_2 \cdot \text{H}_2\text{O}$). The solvent was removed from the solution *in vacuo* leaving a very dark blue solid (7.74 g, 47%). This copper beta-diketonate mixture was highly soluble in organic solvents. For example, a diglyme solution with concentration of 1.6 mole/liter was prepared. This solubility is 17 times larger than the solubility of a
- 20 commonly used precursor, copper(thd)₂ (Hthd=2,2,6,6-tetramethylheptanedione).

A mesitylene solution of the copper beta-diketonate mixture was used for CVD of copper oxide films in an experiment similar to that of Example 1. The stoichiometry of the films depended on the oxygen content of the deposition atmosphere, varying from Cu_2O with no oxygen to CuO for 20% oxygen.

EXAMPLE 31

Synthesis of mixed indium beta-diketonates, $\text{In}(\text{beta-diketonates})_3$. InCl_3 (2.50 g, 11.3 mmol) was dissolved in 40 mL of EtOH and a beta-diketone mixture (6.03 g, 34.4 mmol) diluted with 10 mL of EtOH was added. Smoke was evolved upon dropwise addition of Et_3N (3.50 g, 34.5 mmol) and the solution turned yellow upon further addition. The solution was stirred for 3 hours and the solvent was then removed *in vacuo*. After adding 40 mL of hexane, the solution was filtered and the solvent was removed *in vacuo* leaving a yellow liquid (4.89 g, 67%). The resulting liquid was used in a CVD experiment similar to that of Example 1. An electrically
10 conductive film of indium(III) oxide, In_2O_3 , was deposited.

EXAMPLE 32

Synthesis of mixed dimethyltin(IV) beta-diketonates, $\text{Me}_2\text{Sn}(\text{beta-diketonates})_2$. Me_2SnCl_2 (10.50 g, 47.8 mmol) was dissolved in 30 mL of EtOH and a beta-diketone mixture (10.62 g, 60.2 mmol) diluted with 15 mL of EtOH was added. Smoke was evolved upon dropwise addition of Et_3N (6.12 g, 60.5 mmol) diluted with 15 mL of EtOH and the solution eventually became cloudy. After the addition was complete, the resulting solution was warmed to 95 °C and the precipitate dissolved. A reflux was continued for 12 hours and then the solution was cooled to 25 °C and the solvent was removed *in vacuo*. After most of the volatiles were removed, evacuation
20 was continued at 60 °C for 4 hours. Hexane (60 mL) was then added, the solution was filtered and the solvent was removed *in vacuo* giving a turbid, yellow liquid. This viscous liquid was filtered through densely packed celite giving a clear, yellow liquid (7.16 g, 48%). The resulting liquid was used in a CVD experiment similar to

that of Example 1. An electrically conductive film of tin(IV) oxide, SnO_2 , was produced.

EXAMPLE 33

Synthesis of mixed chromium beta-diketonates, $\text{Cr}(\text{beta-diketonates})_3$. For the following reaction, all manipulations before solvent removal were performed on a benchtop in air. $\text{CrCl}_3 \cdot \text{H}_2\text{O}$ (2.66 g, 15.1 mmol) was dissolved in 100 mL of water. To this was added urea (20.04 g, 333.7 mmol) and then a beta-diketone mixture (10.55 g, 60.3 mmol). On heating, a precipitate formed. The mixture was heated for 12 hours at 100 °C, filtered and then air-dried at ambient temperature. After drying, 20 mL of benzene was added and this was heated to boiling. Then, 75 mL of hot petroleum ether was added carefully and the resulting solution was chilled in an ice bath. On cooling, no crystals formed so the purple solution was filtered and the solvent was removed *in vacuo* to leave an oily solid. On standing, the dark brown mass solidified as a dark purple material (3.98 g, 69%). This solid was dissolved in mesitylene and the resulting solution was used in a CVD experiment similar to that of Example 1. A film of chromium(III) oxide, Cr_2O_3 , was formed.

EXAMPLE 34

Synthesis of the triethylenetetramine adduct of mixed strontium beta-diketonates, $\text{Sr}(\text{beta-diketonates})_2 \cdot \text{teta}$. SrH_2 (4.64 g, 51.8 mmol) was suspended in 30 mL of THF and triethylenetetramine (7.57 g, 51.8 mmol) was added. The suspension was cooled in an ice bath and a beta-diketone mixture (18.24 g, 104.2 mmol) diluted with 30 mL of THF was added dropwise. After the addition was complete, the ice bath was removed and after stirring 2 hours at room temperature the mixture began to heat up and bubble rapidly. Bubbling had subsided after 1 hour, and stirring was

continued another 12 hours. The turbid solution was then filtered through celite and the solvent was removed *in vacuo* to leave a light yellow, viscous liquid (21.16 g, 70%) which was taken up in pmdeta (19.38 g) to give a 52% w/w solution. The resulting solution was used in a CVD experiment similar to that of Example 3. A film of strontium carbonate, SrCO_3 , was formed.

EXAMPLE 35

Synthesis of mixed beta-diketonates of iron(III), $\text{Fe}(\text{beta-diketonates})_3$. Iron(III) tris(acetylacetonate), $\text{Fe}(\text{acac})_3$, (1.10 g, 3.11 mmol) and a beta-diketone mixture (2.46 g, 14.0 mmol) were placed together in a flask and heated to 115 °C. The dark rust-colored solution eventually became darker as it was refluxed for 12 hours. The volatiles were then removed *in vacuo* to leave a very dark brown liquid (1.56 g, 86%). This liquid was used in a CVD experiment similar to that of Example 3. A film of iron(III) oxide, Fe_2O_3 , was formed.


EXAMPLE 36

Synthesis of mixed beta-diketonates of cobalt(III), $\text{Co}(\text{beta-diketonates})_3$. Cobalt(II) carbonate, CoCO_3 , (0.50 g, 4.20 mmol) and a beta-diketone mixture (4.44 g, 25.3 mmol) were placed together in a flask and heated to 100 °C. With vigorous stirring, 10% H_2O_2 (6 mL) was added dropwise resulting in gas and smoke evolving from the dark green solution. After the addition was complete, the solution was slowly cooled to room temperature while gas and smoke were still being generated. After the bubbling had ceased, two 30 mL portions of hexane were used to extract the solution. The volatiles were removed from the resulting solution *in vacuo* giving a dark forest green solid (2.06 g, 84%). This solid was dissolved in


pentamethyldiethylenetriamine, and the resulting solution was used in a CVD experiment similar to that of Example 1. A film of cobalt(III) oxide was formed.

EXAMPLE 37

Synthesis of mixed beta-diketonates of bismuth. Bismuth chloride was first
 5 reacted with lithium bis(trimethylsilyl)amide to form bismuth tris(bis(trimethylsilyl)amide), which was then further reacted with mixed beta-diketones.



4.569g BiCl_3 was dissolved (suspended) in 25 ml THF, and 10.497g
 10 $\text{Li}[\text{N}(\text{SiMe}_3)_2]\text{Et}_2\text{O}$ dissolved in 50 ml THF was cannula transferred to the BiCl_3 at 25 °C. The reaction was exothermic, so a 10 °C water bath was added and addition was continued. The solution became yellow with a colorless precipitate. This was stirred 4 hours at 25 °C with the flask covered with aluminum foil to keep out light from this potentially light-sensitive material. The solvent was stripped off leaving a yellow
 15 powder. 75 ml hexane was added, giving a turbid yellow solution, from which a gray precipitate (LiCl) settled out leaving an orange solution. Filtering and stripping left an orange to light yellow solid which was stored overnight under N_2 with the flask covered by foil. 8.45g of a fine, powdery yellow solid $\text{Bi}[\text{N}(\text{SiMe}_3)_2]_3$ was isolated (85% yield). NMR showed one resonance for the product, plus another resonance
 20 with about the same chemical shift (~ 5-10% intensity) for an unknown species. Some THF was also found (~ 5-10%).



2.73g $\text{Bi}[\text{N}(\text{SiMe}_3)_2]_3$ was dissolved in 20 ml hexane and 2.19g of a beta-diketone mixture in 20 ml hexane was added. This gave a very thick yellow gel. The


solvent was removed and 20 ml THF was added, giving a light yellow solution. Since there was no obvious color change to indicate complete reaction, the solution was refluxed for 3 hours (80 °C). There was still no color change, so the solvent was removed leaving a yellow gel and some solid material. This eventually dried (on
5 further pumping) to a light yellow powder. 2.71 g of light yellow powder (90% yield) was isolated. The solid was dissolved in 30 ml toluene and filtered through celite. A colorless, very gelatinous solid, probably Li(beta-diketonate), was filtered off leaving a yellow, clear solution. This stripped to a slightly sticky, yellow powder (2.26 g). This is an overall yield of 75%. NMR showed a pure product with all the beta-
10 diketone components.

This product was dissolved in pmdeta and the resulting solution used in a CVD experiment similar to that of Example 3. A film of bismuth oxide was produced.

This bismuth precursor can be dissolved in the strontium precursor of Example 15 and the tantalum precursor of Example 9 to form a liquid precursor for the CVD of strontium bismuth tantalate. Many other liquid precursors to multicomponent oxides can be formed by mixing appropriate precursors made according to this invention.

EXAMPLE 38

Example 1 describes one method for the synthesis of beta-diketones. A
20 disadvantage of that method is that the crude product contains impurities (greater than 10 per cent) that may need to be removed by methods such as distillation. Another reaction has been found to yield fewer impurities. It uses sodium amide (sodamide) in place of the sodium hydride of example 1, and an organic acid chloride in place of the ethyl ester of Example 1.



The reactants were prepared as follows: Pinacolone is either purged with nitrogen or degassed using the freeze-pump-thaw method to remove dissolved gases such as O₂ or CO₂. Fresh sodamide (commercial material of 95% purity) is powdered
5 using either a mortar and pestle or a ball mill in an atmosphere of dry nitrogen.
(Caution: Old or discolored sodamide can explode when ground or heated.).

^tBu/ⁿBu beta-diketone was synthesized as follows: Powdered NaNH₂ (33.872 g, 868 mmol, 3.2 eq.) was suspended in 350 mL distilled tetrahydrofuran (THF) and heated to 60 °C. Neat pinacolone (102 mL, 816 mmol, 3 eq.) was added at 4.4
10 mL/min with a syringe pump, causing vigorous gas evolution and solvent "reflux". Halfway through the addition, the solution appeared to be more clear but then became more turbid by the end of addition. After complete addition, the suspended material was colorless and the solution was light yellow. The suspension was stirred at 60 °C for 30 minutes and then evacuated (not full vacuum) for 5 minutes at 60 °C to remove
15 some NH₃. (This step aids in the filtration process.) The suspension was cooled to 25 °C and filtered through dry celite. After filtration, the volatiles were removed *in vacuo* leaving the bulk of the material as a soft mass of light yellow solid (probably a weakly-coordinated THF adduct) and a colorless powder coating the walls of the flask. These solids were dissolved in 350 mL of dry, freshly distilled Et₂O and cooled
20 to 0 °C. Neat 2-methylbutyryl chloride (33 mL, 271 mmol, 1 eq.) was added at 3 mL/min using a syringe pump with vigorous stirring, giving a turbid orange solution. After addition, the cold bath was removed and the reaction was stirred another 10 minutes. The reaction was then quickly poured into a rapidly-stirring mixture of conc. HCl (45 mL, 540 mmol, 2 eq.), 100 g ice and 100 mL water. The layers were

separated and the aqueous layer was washed twice with 50 mL Et₂O. The Et₂O extracts were combined and were then washed twice with 50 mL of sodium bicarbonate solution and then dried over MgSO₄. The suspension was filtered (coarse frit) and the volatiles were removed *in vacuo* leaving a yellow liquid (43.85 g, 88% crude yield, less than 5% impurities by NMR). During distillation at 19 mbar pressure, a 5 mL forerun was collected from 84-88 °C and the product was collected from 88 - 92 °C (31.831 g, 64% purified yield).

The liquids and solutions disclosed in these examples all appeared to be non-pyrophoric by the methods published by the United States Department of Transportation. One test calls for placing about 5 milliliters of the liquid or solution on an non-flammable porous solid, and observing that no spontaneous combustion occurs. Another test involves dropping 0.5 milliliters of the liquid or solution on a Whatman No. 3 filter paper, and observing that no flame or charring of the paper occurs.

Some of the precursors appear to be non-reactive to atmospheric oxygen and water vapor; these air-stable precursors include those for aluminum (Example 1), ruthenium (Example 18), cerium (Example 27), copper (Example 30), indium (Example 31), chromium (Example 33), iron (Example 35) and cobalt (Example 36). The other precursors generally react with ambient air, and should be stored under a dry inert, atmosphere such as nitrogen.

Those skilled in the art will recognize or be able to ascertain using no more than routine experimentation, many equivalents to the specific embodiments of the invention described specifically herein. Such equivalents are intended to be encompassed in the scope of the following claims.

What is claimed is:

1. A composition for use in the formation of metal oxides, comprising:
a mixture of metal beta-diketonates, said metal beta-diketonates containing
one or more metal types and two or more beta-diketonate types, in which at least one
of the metal beta-diketonates contains two or more types of beta-diketonate ligand
5 bound to the metal.
2. The composition of claim 1, in which the composition of matter is a
liquid at 20 °C.
3. The composition of claim 1, in which the composition of matter is
highly soluble in organic solvents.
- 10 4. The composition of matter as in claims 1, 2 or 3 in which the beta-
diketonate ligands are chosen from those listed in Table 1 of the specification.
5. The composition of claim 1, wherein the beta-diketonate has the
formula, $R^1C(=O)CHR^3C(=O)R^2$, , where R^1 and R^2 may be an alkyl group, a
fluoroalkyl group or an alkyl group containing oxygen- or nitrogen-containing species
15 (for example, an amino, alcohol or alkoxyl species); and R^3 may be an alkyl group, a
fluoroalkyl group or an alkyl group containing oxygen- or nitrogen-containing species
or H.
6. The composition of claim 6, wherein the alkyl group of R^1 , R^2 or R^3
contains less than ten carbons.
- 20 7. The composition of claim 6, wherein the alkyl group of R^1 , R^2 or R^3
contains less than seven carbons.
8. The composition of claim 1, 2 or 3 in which the metal or metals are
selected from the group consisting of zinc, cadmium, mercury, aluminum, gallium,
indium, thallium, tin, lead, antimony, bismuth, lithium, sodium, potassium, rubidium,

cesium, beryllium, magnesium, calcium, strontium, barium, scandium, yttrium,
lanthanum, titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium,
molybdenum, tungsten, manganese, technetium, rhenium, iron, ruthenium, osmium,
cobalt, rhodium, iridium, nickel, palladium, platinum, copper, silver, cerium, the other
5 rare earth metals and the actinide metals.

9. The composition of claim 8 in which the metal or metals are selected
from the group consisting of barium, strontium, calcium, magnesium, aluminum,
titanium, zirconium, vanadium, niobium, tantalum, chromium, molybdenum,
manganese, iron, ruthenium, cobalt, nickel, copper, zinc, indium, tin, lead, bismuth,
10 yttrium, lanthanum and cerium .

10. The composition of claim 1, wherein the mixture comprises at least
four types of beta-diketonate.

11. The composition of claim 1, wherein the mixture comprises at least six
types of beta-diketonate.

15 12. A compound for use in the formation of metal oxides, comprising:
a metal beta-diketonate containing two or more types of beta-diketonate ligand
bound to the metal.

13. The composition of claim 12, in which the composition of matter is a
liquid at 20 °C.

20 14. The composition of claim 12, in which the composition of matter is
highly soluble in organic solvents.

15. The composition of claim 12, 13 or 14 in which the beta-diketonate
ligands are chosen from those listed in Table 1 of the specification.

16. The composition of claim 12, wherein the beta-diketonate has the formula, $R^1C(=O)CHR^3C(=O)R^2$, , where R^1 and R^2 may be an alkyl group, a fluoroalkyl group or an alkyl group containing oxygen- or nitrogen-containing species (for example, an amino, alcohol or alkoxyl species); and R^3 may be an alkyl group, a fluoroalkyl group or an alkyl group containing oxygen- or nitrogen-containing species or H.

17. The composition of claim 16, wherein the alkyl group of R^1 , R^2 or R^3 contains less than ten carbons.

18. The composition of claim 16, wherein the alkyl group of R^1 , R^2 or R^3 contains less than seven carbons.

19. A process for forming a metal-containing film, comprising:-
providing a mixture of metal beta-diketonates, said metal beta-diketonates containing one or more metal types and two or more beta-diketonate types, in which at least one of the metal beta-diketonates contains two or more types of beta-diketonate ligand bound to the metal; and
contacting the mixture to a surface in a deposition process to deposit a metal-containing material.

20. The process of claim 19 in which the deposited material comprises one or more metal oxides.

21. The process of claim 19 in which the metal or metals are selected from the group consisting of barium, strontium and titanium.

22. The process of claim 19 in which the metal or metals are selected from the group consisting of strontium, bismuth, niobium and tantalum.

23. The process of claim 19, wherein a sol-gel process is used to deposit material containing one or more metals or metal oxides.

24. The process of claim 19, wherein a spray-coating or spin-coating process is used to deposit material containing one or more metals or metal oxides.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/07829

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C07F19/00 C23C16/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C07F C23C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CHEMICAL ABSTRACTS, vol. 103, no. 12, 23 September 1985 Columbus, Ohio, US; abstract no. 93770, MALHOTRA, R. K. ET AL: "Synergism in the extraction of uranium(VI) by a mixture of oxine and beta.-diketones" XP002070941 see abstract & PROC. - INDIAN ACAD. SCI., CHEM. SCI. (1985), 94(3), 515-19 CODEN: PIAADM; ISSN: 0253-4134, 1985, --- -/-	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

9 July 1998

Date of mailing of the international search report

20/08/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Rinkel, L

INTERNATIONAL SEARCH REPORT

Int. .tional Application No

PCT/US 98/07829

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CHEMICAL ABSTRACTS, vol. 71, no. 8, 25 August 1969 Columbus, Ohio, US; abstract no. 33898, WOO, CHING-HUNG: "Extractions of several rare earths using a combination of thenoyltrifluoroacetone and acetylacetone" XP002070942 see abstract & U. S. AT. ENERGY COMM. (1968), ORO-2124-18, 94 PP. AVAIL.: DEP.:CFSTI FROM: NUCL. SCI. ABSTR. 1969, 23(7), 11605 CODEN: XAERAK, 1968,	1
A	EP 0 527 661 A (THE ASSOCIATED OCTEL COMPANY LIMITED) 17 February 1993 see the whole document	1-24

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/07829

Patent document cited in search report	Publication date	Patent family- member(s)	Publication date
EP 527661 A	17-02-1993	AU 658922 B	04-05-1995
		AU 2437692 A	16-03-1993
		CA 2113715 A	04-03-1993
		WO 9304072 A	04-03-1993
		JP 7500318 T	12-01-1995
		NO 940471 A	13-04-1994